



Polycast[®] Medical Grade PMMA

(formerly Glasflex)

IMPLANTABLES

- Biocompatible*
- Proven lot traceability
- Polycast[®] provides clarity for better placement of implant
- Custom manufacturing
- FDA masterfile on all medical materials

APPLICATIONS

- Orthopedic implants
- Craniomaxillofacial (CMF) implants
- Distal Centralizers
- Implantable sensors for CGM (continuous glucose monitor)
- Intraocular lens implants

CAST ACRYLIC SHEET, RODS & TUBES

- PMMA products for medical applications and devices
- Acrylic suitable for high precision machining**

APPLICATIONS

- Custom Orthotics (POLYDOR*)
- Reservoirs for medical devices and imaging machines
- Fluidic manifolds used for diagnostics and analytical instruments

POLYCAST FDA GRADE ACRYLIC SHEET

- For use in manufacturing food and beverage dispensing equipment
- Certified colors: Clear, White, Green, Red, Blue***



POLYCAST FDA



Call 800-677-4338 or email marketing@spartech.com to order these products.

FOLLOW US:

Summary of Typical Properties of PMMA Sheet & Rod

PROPERTY	TEST METHODS	SHEET				ROD	
		POLYCAST FDA GRADE NSF Certified	UVA 400	UVA 400-NCL	UVA 400-LCL	PMMA MEDICAL ROD #2	PMMA MEDICAL ROD #3
Monomer Content	Gas Chromatography	–	No Greater Than 0.8%	No Greater Than 0.8%	No Greater Than 0.8%	No Greater Than 0.8%	No Greater Than 0.8%
Refractive Index	ASTM D542	1.49	1.49	1.49	1.49	1.49	1.49
Specific Gravity	ASTM D792	1.19	1.19	1.19	1.19	1.19	1.19
Rockwell Hardness	ASTM D785	M-98	M-94	M-94	M-94	M-94	M-94
Tensile Strength (Rupture)	ASTM D638	11,250 PSI	9,000 PSI	9,000 PSI	9,000 PSI	9,000 PSI	9,000 PSI
Flexural Strength (Rupture)	ASTM D790	15,000 PSI	15,000 PSI	15,000 PSI	15,000 PSI	15,000 PSI	15,000 PSI
Compression Strength (Yield)	ASTM D695	18,000 PSI	18,000 PSI	18,000 PSI	18,000 PSI	18,000 PSI	18,200 PSI
Impact Strength (Izod Unnotched – ft. lbs./in.)	ASTM D256	0.375	4.2	4.2	4.2	4.2	4.2
Haze	ASTM D1003	Less Than 0.5%	Less Than 0.5%	Less Than 0.5%	Less Than 0.5%	Less Than 0.5%	Less Than 0.5%
UV Transmission		0% @ 320 nm	10% @ 370 nm	Less Than 10% @ 400 nm	Less Than 10% @ 400 nm	10% @ 370 nm	85% @ 370 nm
Visible Light Transmission	ASTM D1003	92%	92%	92%	92%	92%	92%
Molecular Weight		–	2 Million	Greater Than 2 Million	Infinite	Infinite	2 Million
Solvent Resistance	Weight gain in acetone (24 hours/22°)	–	2%	170%	19%	2%	170%
Water Absorption	ASTM D570	0.35%	0.35%	0.35%	0.35%	0.35%	0.35%

Spartech Polycast manufactures medical grade PMMA cast acrylic products for the medical device community using Good Manufacturing Practice (GMP). Intended applications include implantable intraocular lenses and cement spacers for orthopedic prostheses.

Biocompatibility studies were performed by an independent laboratory using Good Laboratory Practice (GLP) regulations. This information is supported by certified results of extensive clinical scientific data. All information is included in our FDA Master File # MAF-300, which is held under the custodianship of the FDA and authorization can be granted upon request.

The following clinical tests were performed to establish the biocompatibility of these materials, as outlined by the FDA.

- Hemolysis test by Extraction Method
- Hemolysis test by Direct Contact
- Salmonella/Mammalian Mutagenicity Test
- Cytotoxicity test using the Agarose Overland Method
- Guinea Pig Maximization test of Biomaterial Extracts (Magnusson and Kligman) with added positive controls
- USP Systemic Toxicity Study in Mice
- USP Intracutaneous Toxicity test in the Rabbit
- Inhibition of Cell Growth, 9 Point Assay
- Accelerated Extractables
- Physicochemical - USP tests
- Residual Monomer GC
- Infrared Analysis
- Ultraviolet and UV Visible Spectra
- Gel Permeation HPLC (Molecular Dispersion)

TEST	METHOD	RESULT
1. Cytocompatibility Study	(MEM) (L-929) / 72 Hrs. (SC) (AS) + (cso) / 24Hrs. (SC) (AS) (CSOO + extracts for Acute systemic toxicity)	No Lysis or Cytotoxicity Effect No Cell Lysis No Toxicity
a. Extract		
b. Direct Contact Saline-blood Mixture	Direct Contact with Lysis	No Blood Cell
c. Cell Attachment	L-929	Non Toxic
2. Mutagenicity	AMES (Vitro)	Not Mutagenic
3. Systemic Toxicity Extract in Mouse	USP-TUO12-500	No Considerable Toxicity
4. Rabbit Intradermal Injection of Extract	Erythema Edema	None None
5. Sensitization	By DNCB	Good Sensitization
6. Implantation Test		No Reaction
a. Intramuscular		
b. Implantation Test 4-Week		
7. Equivalence Evaluation and Toxicological Risk Assessment	USP Class VI and ISO 10993 Guidelines	Demonstrated chemical and toxicological equivalence among all UVA 400 materials



Polycast® sheet products are ISO 9001 certified.



REV 3/2024

11650 Lakeside Crossing Ct. • Maryland Heights, MO 63146 • 800-677-4338 • www.spartech.com

Copyright ©2024, Spartech, LLC. Spartech makes no representations, guarantees, or warranties of any kind with respect to the information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Spartech makes no warranties or guarantees respecting suitability of either Spartech's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. SPARTECH MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or product reflected by the information. This literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.