

# 1558 Cellulose Acetate

Sheeting – P/P

## Product Description

Clear Cellulose Acetate – Polished surfaces. This material is designed to meet the requirements of ANSI Z87.1 and LP-504 Type I.

## Technical Properties

| Property                         | Test Method | Value                    |
|----------------------------------|-------------|--------------------------|
| Thickness                        | ASTM D-792  | 0.042                    |
| Tensile Strength                 | ASTM D-882  | 5,400 psi                |
| Tensile Elongation               | ASTM D-882  | 40.0%                    |
| Water Absorption (24 hrs @ 23°C) | ASTM D-570  | 4.0%                     |
| Light Transmission               | ASTM D-1003 | 88%                      |
| Flammability                     | ASTM D-568  | 0.4 In <sup>2</sup> /sec |
| Flammability                     | ASTM D-635  | 1.7 In/Min               |

For additional information, please contact Spartech at 800-677-4338 (800-67-SHEET), e-mail [info@spartech.com](mailto:info@spartech.com) or visit our website at [www.spartech.com](http://www.spartech.com)

Customers are responsible for determining whether products and information are appropriate for their use, including the evaluation of all applicable laws. Spartech LLC assumes no liability for the accuracy or completeness of information contained herein, and such information is subject to change without notice. All products supplied are subject to the standard terms and conditions of sale of Spartech LLC. **NO WARRANTY OF ANY KIND, EITHER EXPRESS OR IMPLIED, IS MADE BY THIS TECHNICAL DATA SHEET. ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.**