

# GFPP

15% Glass Filled Polypropylene

## Product Description

A UV Stabilized PP compound optimized for high impact resistance.

## Technical Properties

Property	Test Method	Value*
Specific Gravity	ASTM D-792	1.01
Tensile Strength	ASTM D-638	6950 psi
Flexural Modulus	ASTM D-790	390,000 psi
Flexural Strength	ASTM D-790	10,150 psi
Heat Deflection Temperature (@264 psi)	ASTM D-648	228°F

For additional information, please contact Spartech at 800-677-4338 (800-67-SHEET), e-mail [info@spartech.com](mailto:info@spartech.com) or visit our website at [www.spartech.com](http://www.spartech.com)

Customers are responsible for determining whether products and information are appropriate for their use, including the evaluation of all applicable laws. Spartech LLC assumes no liability for the accuracy or completeness of information contained herein, and such information is subject to change without notice. All products supplied are subject to the standard terms and conditions of sale of Spartech LLC. **NO WARRANTY OF ANY KIND, EITHER EXPRESS OR IMPLIED, IS MADE BY THIS TECHNICAL DATA SHEET. ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.**