

Royalite® R559

Fire-rated sheet

Product Description

Royalite R559 is a flame rated, UL listed 94V-0 and 94 5V, extruded sheet product manufactured from recycled PVC/ABS resin. The excellent balance of physical and mechanical properties, combines with its flame rating, make R559 an excellent, cost effective choice for a wide variety of applications in the electronics, equipment, and materials handling industries.

Technical Properties

Property	Test Method	Value*
Specific Gravity (color dependent)	ASTM D-792	1.18 - 1.25
Tensile Strength	ASTM D-638	4,600 psi
Flexural Strength	ASTM D-790	7,400 psi
Flexural Modulus	ASTM D-790	270,000 psi
Izod Impact (Notched) 72°F	ASTM D-256	5.5 ft-lbs/in
Rockwell Hardness (R Scale)	ASTM D-785	91
Heat Deflection Temperature (@ 264 psi - annealed)	ASTM D-648	175°F
Coefficient of Linear Thermal Expansion	ASTM D-696	4.6 - 5.5x10 ⁻⁵ in/in/°F
Mold Shrinkage	Internal	0.005 - 0.007 in/in
Motor Vehicle Safety Standard	FMVSS 302	Passes
Flammability	UL 94 V-0	Listed @ 0.091"
Flammability	UL 94-5VA	Listed @ 0.091"

*All values based on 0.125" unless otherwise stated

For additional information, please contact Spartech at 800-677-4338 (800-67-SHEET), e-mail info@spartech.com or visit our website at www.spartech.com

Customers are responsible for determining whether products and information are appropriate for their use, including the evaluation of all applicable laws. Spartech LLC assumes no liability for the accuracy or completeness of information contained herein, and such information is subject to change without notice. All products supplied are subject to the standard terms and conditions of sale of Spartech LLC. **NO WARRANTY OF ANY KIND, EITHER EXPRESS OR IMPLIED, IS MADE BY THIS TECHNICAL DATA SHEET. ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.**