

SoundX EVA

Flexible Acoustical Barrier

Product Description

SoundX solutions provide customers with a flexible sheet for sound abatement applications. The high specific gravity of this mass-loaded solution allows SoundX to absorb sound waves and prevent the transmission of sound. It has excellent cold temperature flexibility and is perfect for low to medium draw, thermoformed engine and firewall partitions. Additionally, SoundX EVA can be easily compression molded or die cut to fit most sound abatement applications.

Technical Properties

Property	Test Method	Value
Specific Gravity	ASTM D-792	1.80
Hardness - Shore A	ASTM D-2240	85
Tensile Strength - Die C	ASTM D-412	MD 250 psi, A MD 250 psi
Tear Strength - Die C	ASTM D-624	MD 85 psi, A MD 85 psi

For additional information, please contact Spartech at 800-677-4338 (800-67-SHEET), e-mail info@spartech.com or visit our website at www.spartech.com

Customers are responsible for determining whether products and information are appropriate for their use, including the evaluation of all applicable laws. Spartech LLC assumes no liability for the accuracy or completeness of information contained herein, and such information is subject to change without notice. All products supplied are subject to the standard terms and conditions of sale of Spartech LLC. **NO WARRANTY OF ANY KIND, EITHER EXPRESS OR IMPLIED, IS MADE BY THIS TECHNICAL DATA SHEET. ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.**