

# TPR BLEND 3

## Flexible Sheet

### Product Description

TPR Blend 3 is a lightweight, low density solution for automotive non-carpet liners and matting products. Our specialty formulated sheet incorporates 25 years of experience in the North American automotive liner and matting flooring aftermarket. TPR Blend 3's advanced characteristics provide customers a lightweight, durable solution.

### Technical Properties

Property	Test Method	Value
Specific Gravity	ASTM D-792	0.96
Hardness - Shore A	ASTM D-2240	98
Tensile Strength - Die A	ASTM D-412	MD 1,400 psi, AMD 1,320 psi
Ultimate Elongation - Die A	ASTM D-412	MD 1,100%, AMD 1,120%
Tear Strength - Die C	ASTM D-624	MD 330 psi, AMD 360 psi
Izod Impact (Notched) 72°F	ASTM D-256	No Break
Vicat Softening Temperature	ASTM D-1525	180 °F
Fogging	SAE J1756	91 Fn
Flammability	FMVSS 302	MD <25 mm/min, AMD <20 mm/min

For additional information, please contact Spartech at 800-677-4338 (800-67-SHEET), e-mail [info@spartech.com](mailto:info@spartech.com) or visit our website at [www.spartech.com](http://www.spartech.com)

Customers are responsible for determining whether products and information are appropriate for their use, including the evaluation of all applicable laws. Spartech LLC assumes no liability for the accuracy or completeness of information contained herein, and such information is subject to change without notice. All products supplied are subject to the standard terms and conditions of sale of Spartech LLC. **NO WARRANTY OF ANY KIND, EITHER EXPRESS OR IMPLIED, IS MADE BY THIS TECHNICAL DATA SHEET. ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.**